

ULTIPURA MR-BW 8050

Water based release agent for cold cured polyurethane foam.

PROPERTIES

- ✓ Recommended dilution from 1:2 to 1:4 into soft or demineralised water.
- ✓ Ready-use, environmentally friendly releasing agent for the production of MDI based flexible PU foams manufactured by cold curing process.
- ✓ If tested it may be used for TDI or MDI/TDI blends.
- ✓ Relatively dry touch.
- ✓ High slippery power.
- ✓ Non hazardous for health and environment.
- ✓ Excellent release and lubricity
- ✓ Excellent anti-noise characteristics.
- ✓ Negligible mould build-up.

CHARACTERISTICS

APPEARANCE:	White emulsion (cationic)
Ph VALUE :	5-7
FILM:	Soft
SOLVENTS:	No solvent
STABILITY:	Stable
FLASH POINT:	< 0 °C-
PACKAGING:	Drum of Kg 45

APPLICATION

Concentrate for dilution.

Air-gun:

Nozzle size: 0.5 - 0.9 mm for small/medium moulds, 0.5-0.8 mm for large moulds.

STORAGE

After long term storage, this product should be moderately agitated before use. Preferably between 5-40 °C in tightly closed original packings. If exposed to temperatures below 15 °C this product should be acclimatised at room temperature for 24 hrs. before use. Shelf life is 8 months if stored as indicated.

Our products are manufactured under strict control to insure the best quality and performance. Zurechem undertakes no responsibility whatsoever. Statements contained herein should not be considered as a warranty of any kind, expressed or implied. No liability is accepted for the infringement of any patent.